

PE2000+MoS2 - Polyethylene 2000 + MoS2

Other material names PE2000+MoS2: PE-UHMW with MoS2, Moly, Molybden disulfid

Material group: Polyethylene

The material is based on high molecular weight polyethylene. This material is self-lubricating and has a low sliding friction coefficient. The good sliding properties of the core product PE2000 have been improved even further. This involved improving already impressive material properties. For example, the self-lubricating character of this material has resulted in an improved sliding friction coefficient in comparison with PE1000. Material is ideally suited for use in sliding guides, slide segments, and slide bearings.

Color of material:

Gray



Typical applications:

- chain and belt running guides
- conveying and slide elements
- friction bearings
- cogwheels and drive wheels
- turnaround wheels and curved tracks



The material is used in:

Beverage industry
Food industry
Automobile industry

Features:

- Self-lubricating - lower sliding friction coefficient
- Increased wear resistance
- Excellent impact/shock resistance
- Good resistance to chemicals
- Good anti-adhesion properties
- Electrically isolating
- Better resistance to UV rays than PE1000 green/natural

Material availability: Some sizes are in stock

Material properties table

Specific weight	0.95 g/cm ³
Yield strength	17 N/mm ²
Tensile strength	33 N/mm ²
Allowable mean pressure deformation 1%	4.00 N/mm ²
Allowable mean pressure deformation 2%	7.50 N/mm ²
Allowable mean pressure deformation 5%	13.50 N/mm ²
p.v dry limit	0.08 MPa.m/s

Tensibility	350 %
Tensile modulus	750 N/mm ²
Impact toughness	bez zlomu
Notched toughness	>120 kJ/m ²
Ball hardness	40 N/mm ²
Friction coefficient	0.08
Sliding wear	0.04 um/km
Abrasive wear	80
Antistatic material	No
Permittivity	2.10
Electrical strength	45 kV/mm
Specific internal resistance	10 ⁽¹²⁾ Ω
Specific surface resistance	10 ⁽¹²⁾ Ω.cm
Melting point	135 °C
Thermal expansion	20 10 ⁽⁻⁵⁾ /K
Thermal conductivity	0.41 W/(K.m)
Permanent use temperature	-200 ; 80 °C
Transient temperature of use	-200 ; 90 °C
Absorbability	0,01 %
Water absorption	0,1 %
Resistance - oils	resistant
Acid resistance	resistant
Durability - alcali	resistant
Food contact	No

Engineering plastics are supplied in the form of bars, plates, strips, tubes and sheets. From the semi-finished products the company TechPlasty has regularly in stock, we also supply blanks.

All standard and special materials are designed to meet your specific requirements. Their mechanical, thermal, and electrical properties and chemical resistance satisfy the most demanding requirements and this allows them to work even in the most difficult conditions. If you need advice when choosing the appropriate material for your application, please contact us. We'll gladly advise you. You can utilize the long-term experience of our technical advisors free-of-charge, who can visit you right in your operation and solve your requirements for engineering plastics directly at the site of their usage.

TechPlasty, s.r.o.

Kysucká 7/A
010 01 Žilina
Slovakia

